



# VESTA FR

fire-rated no added urea-formaldehyde resin particleboard



## THE PARTICLEBOARD SOLUTION OF CHOICE FOR FIRE SAFETY NEEDS

VESTA FR particleboard is the no added urea-formaldehyde resin option for building code and project specifications that require fire safety compliance. VESTA FR is a UL approved, Class A/Class 1 fire-rated panel that is ideal for interior, non-structural use in restaurants, schools, hotels, malls, airports, offices and public buildings.

### VESTA FR offers:

- Superior strength and dimensional stability
- Low linear expansion and thickness swell
- Smooth surface properties for laminating and finishing
- Easy machining and low tool wear
- Wide range of products and sizes

### LEED Qualifying Credits:

- MR 4.1 Recycled Content 10%
- MR 4.2 Recycled Content 20%
- MR 5.1 Regional Materials 10%
- MR 5.2 Regional Materials 20%
- MR 7 Certified Wood
- IEQ 4.4 Low-emitting Materials

### VESTA FR Particleboard Specification (Albany, OR)

Grade	VESTA FR Particleboard	
Thickness (in)*	3/8 - 3/4	13/16 - 1 1/2
Specification	Class A/Class 1 Flame Spread	Class A/Class 1 Flame Spread
Density (pcf)	47 - 50	44 - 47
MOR (psi)	1,600	1,600
MOE (psi)	300,000	250,000
Internal Bond (psi)	80	60
Face Screw Hold (lb)	250	250
Edge Screw Hold (lb)	225	175
Linear Expansion (%)	0.40	0.35
Thickness Tolerance (in)	+/- .005	+/- .005
Length and Width (in)	+/- 1/16	+/- 1/16
Squareness (in)	+/- 1/8	+/- 1/8

\* Metric thickness available. The above properties are based on averages of normal production.

- Complies with CPA EPPS 3-08 and CCR 93120.2(a) (CARB Composite Wood ATCM Phase 1 Formaldehyde Emission Limits)
- Material Safety Data Sheets are available upon request
- All panels are approved for use in interior, non-structural applications
- Contains 100% Recycled/Recovered Wood Content
- Conforms to formaldehyde emission requirements for particleboard in ANSI A208.1-2009 Table B and HUD 24 CFR Part 3280

### APPLICABLE STANDARD TESTS

- ASTM E 84 Standard Test for Surface Burning Characteristics of Building Materials
- ASTM C 236 Guarded Hot Box Test
- UL 723 Test for Surface Burning Characteristics of Building Materials

### BUILDING CODES

- ICC - International Code Council - 2000, 2003, 2006 International Building Code
- NFPA - National Fire Protection Association - NFPA 101 Life Safety Code - NFPA 5000 Building Construction Safety Code

### AGENCY APPROVALS

California State Fire Marshall 2660-1627:100, City of New York MEA 177-78-M, City of Los Angeles RR 24811

Underwriter's Laboratories, Inc. Classified Wood Particleboard Surface Burning Characteristics, UL 723 (Based on 100 for Untreated Red Oak)

Flame Spread	20 USA	25 Canada
Smoke Developed	25 USA	25 Canada

### Thermal Conductivity (k) and Thermal Resistance (1/k = R)¹

Thickness (in)	3/8"	1/2"	3/4"	1"
k	0.54	0.62	0.55	0.69
R	1.85	1.16	1.82	1.45

### USAGE NOTES

Some laminates applied to VESTA FR particleboard may change the flame spread rating. Standard available woodworking glues have been successfully used in lamination. However, some adhesives may have compatibility problems with the chemical system used to manufacture VESTA FR particleboard. Any adhesive should be tested for compatibility with the chemical system in VESTA FR particleboard prior to full-scale gluing. Questions should be directed to the glue supplier. When using VESTA FR particleboard in wall systems, an integral vapor barrier must be a properly installed component of the wall in any of the following conditions: the wall has an exterior side and the wall separates spaces conditioned unequally. Joints between panels to be designed to accommodate movement of up to .40 percent. Splined or articulated joints for reveals per AWI Section 500, 500A-G-4 "Joints and Transitions" or similar is suggested.

### STORAGE AND HANDLING

VESTA FR particleboard should never be stored or used outdoors. The indoor storage area should be clean, dry, well ventilated, and free of dust, dirt or particles that could contaminate the particleboard. Store flat on stickers on a level, hard, dry surface. Constant relative humidity and temperature should be maintained. Before use, allow to stabilize to the same conditions as are expected after the panel is installed. Condition 48 to 72 hours prior to lamination. For more information, see Composite Panels Association Technical Bulletin: Storage and Handling of Particleboard and MDF.

VESTA FR | fire-rated no added urea-formaldehyde resin particleboard

www.flakeboard.com 1.800.268.9830



The mark of responsible forestry  
SW-COC-000444  
© 1996 FSC



CPA-3-08 Specification  
California ARB Approved  
Third Party Certifier: TPC-1

