

TFM PERFORMANCE STANDARDS

Properties	Test Method / Standard Reference	Flakeboard TFM Products
Boiling Water Resistance	NEMA LD3-2005 - 3.5	No to slight effect
Impact Resistance	NEMA L3-2005 - 3.8	15 inches
Light Resistance	NEMA LD3-2005 - 3.3	No to slight effect
Scratch Resistance	EN 438 2.14.91 NEMA LD3-2005 - 3.7	3.4N 2.0N
Cleanability / Stain Resistance	NEMA LD3-2005 - 3.4	1-10 - No effect 11-15 - Slight effect
Steam Test	EN 438 2.24	2.5° - 3.5° C
Surface Wear Resistance	NEMA LD3-2005 - 3.13	Solid Colors 400 cycles Woodgrains & Abstract Designs 150 cycles

FLAME SPREAD RATING



Flakeboard Particleboard and MDF treated with fire-retardant (FR) additives are certified by Underwriters Laboratories to have a Class A or Class I flame spread rating. In addition, TFM laminated on Flakeboard's fire-rated particleboard or MDF substrates at the St. Stephen, NB or Simsboro, LA laminating facilities are classified by Underwriters Laboratories to have a Class A or Class I flame spread rating.

HOW TO SPECIFY FLAKEBOARD TFM

Description	Example
Product / Substrate	Duraflake® FR (fire-rated)
Design Code	WF108
Design Name	Kashmir Cherry
Texture	Suede
Panel Dimensions (Thickness / Width / Length)	¾" x 49" x 97"